

SINOWIN NEW MATERIALS CO LTD  
 Hongyun Street No. 20  
 Chong he he bo qiao Village  
 Qingxi town  
 Dongguan Guangdong 523000 CN

**GM650**

Liquid Crystal Polymer (LCP), furnished as pellets

Flammability	Value	Test Method
Flame Rating		
0.8 mm	V-0 (BK)	IEC 60695-11-10
3.2 mm	V-0 (BK)	IEC 60695-11-10
Thermal	Value	Test Method
RTI Imp		
0.8 mm	50 °C	UL 746B
3.2 mm	50 °C	UL 746B
RTI Str		
0.8 mm	50 °C	UL 746B
3.2 mm	50 °C	UL 746B
RTI Elec		
0.8 mm	50 °C	UL 746B
3.2 mm	50 °C	UL 746B



Go To UL iQ Link (<https://iq.ul.com/ul/cert.aspx?ULID=101685429>)

Report Date: 2013-10-17  
 Last Revised: 2017-08-16

此数据表中的信息由塑库网 (<https://www.plasdata.com>) 从该材料的生产商处获得。塑库网尽最大努力确保此数据的准确性。但是塑库网对这些数据值不承担任何责任，并强烈建议在最终选择材料前，就数据值与材料供应商进行验证。