

Component - Plastics

E207780

Guide Information

SABIC JAPAN L L C

PACIFIC GRADES - RESIN, 2-2 KINUGAOKA, MOKA-SHI TOCHIGI-KEN 321-4392 JP

923X(X)

PC/Siloxane "Lexan", furnished as pellets

Color	Min. Thk (mm)	Flame Class	HWI	HAI	RTI Elec	RTI Imp	RTI Str
(X)	1.5	V-0	3	1	125	110	120
	3.0	V-0, 5VA	2	0	125	115	125

Comparative Tracking Index (CTI): 3
Dielectric Strength (kV/mm): 24

Inclined Plane Tracking (IPT) kV: -
Volume Resistivity (10^x ohm-cm): 16

High-Voltage Arc Tracking Rate (HVTR): -

High Volt, Low Current Arc Resis
(D495): -

Dimensional Stability (%): -

(X) - All colors except natural.

NOTE - Material designation may be followed by a color nomenclature consisting of either an alpha/numeric or numeric/alpha combination.

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report
Date: 2002-08-15
Last
Revised: 2018-06-26

© 2019 UL LLC

**IEC and ISO Test Methods**

Test Name	Test Method	Units	Thk (mm)	Value
Flammability	IEC 60695-11-10, IEC 60695-11-20	Class (color)	1.5	V-0 ((X))
			3.0	V-0, 5VA ((X))
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	°C	1.5	960
			3.0	960
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	°C	1.5	825
			3.0	825
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	CTI150
		Material Group	-	IIIb
IEC Ball Pressure	IEC 60695-10-2	°C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	°C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m ²	-	-
ISO Izod Impact	ISO 180	kJ/m ²	-	-
ISO Charpy Impact	ISO 179-2	kJ/m ²	-	-